


1. RAFM and ODS steels for ITER TBM and China DEMO


CLF-1: Fe8.5Cr1.5W0.25V0.1Ta0.5Mn0.1C

CLAM: Fe9Cr1.5W0.2V0.15Ta0.45Mn0.1C





**RAFM
STEELS,
(SWIP,
INEST)**

**ODS-
RAFM
(USTB
etc.)**




➤ Two kinds of RAFM steel (CLF-1, CLAM) are developed for ITER-TBM and DEMO reactor.

➤ 9Cr-ODS steel with fine nano-particles is developed



USTB work

2. Vanadium alloys for advanced blanket







➤ 30kg V-4Cr-4Ti alloy was developed with high purity

Cr (%)	Ti (%)	C (%)	N (%)	O (%)	S (%)
3.81	3.92	0.013	0.002	0.027	0.002
Al (%)	Si (%)	K (%)	Fe (%)	Mg (%)	Ca (%)
0.01	0.059	0.005	0.0053	0.0022	0.0067

**VANADIUM
ALLOYS**


(SWIP)

➤ Carbide dispersion strengthened V-alloys are developed. Ti_3SiC_2 is found to strengthen the V-alloy most efficiently, for both RT and high temperatures .




3. Tungsten alloys/coatings and divertor mock-up development

➤ ODS W-alloy and W coating were developed



Recrystallization temperature of ODS W-alloy is higher than 1750°C.

Electro-deposition metallic W coatings 398 MW/m²




ODS W-ALLOYS (ISSP, USTB)

W COATING (XTC, USTB)

W MOCKUP (SWIP, XTC)


CVD-W/ graphite mock-up



➤ CVD W/graphite and W/Cu mock-ups were developed and tested under high heat flux.

1000 cycles, 10MW/m² HHFT, No failure



EB Fast brazed W/Cu mock-up was developed



4. Functional materials for ITER-TBM

**TRITIUM MULTIPLIER
(SWIP)**

**NEUTRON BREEDER
(SWIP)**



➤ Developed Li_4SiO_4 tritium breeder and neutron multiplier pebbles for ITER-TBM.

➤ Tested their thermal-mechanical properties

